

Document made available under the Patent Cooperation Treaty (PCT)

International application number: PCT/US05/000487

International filing date: 07 January 2005 (07.01.2005)

Document type: Certified copy of priority document

Document details: Country/Office: US
Number: 60/535,330
Filing date: 09 January 2004 (09.01.2004)

Date of receipt at the International Bureau: 18 February 2005 (18.02.2005)

Remark: Priority document submitted or transmitted to the International Bureau in compliance with Rule 17.1(a) or (b)



World Intellectual Property Organization (WIPO) - Geneva, Switzerland
Organisation Mondiale de la Propriété Intellectuelle (OMPI) - Genève, Suisse

1282502

THE UNITED STATES OF AMERICA

TO ALL TO WHOM THESE PRESENTS SHALL COME:

UNITED STATES DEPARTMENT OF COMMERCE

United States Patent and Trademark Office

February 08, 2005

THIS IS TO CERTIFY THAT ANNEXED HERETO IS A TRUE COPY FROM THE RECORDS OF THE UNITED STATES PATENT AND TRADEMARK OFFICE OF THOSE PAPERS OF THE BELOW IDENTIFIED PATENT APPLICATION THAT MET THE REQUIREMENTS TO BE GRANTED A FILING DATE.

APPLICATION NUMBER: 60/535,330

FILING DATE: *January 09, 2004*

RELATED PCT APPLICATION NUMBER: *PCT/US05/00487*



Certified by

Under Secretary of Commerce
for Intellectual Property
and Director of the United States
Patent and Trademark Office

010904
16523 U.S. PTO

Docket Number 3253

**IN THE UNITED STATES PATENT AND TRADEMARK OFFICE
PROVISIONAL APPLICATION COVER SHEET**

31353 U.S. PTO
60/535330
010904

Mail Stop Provisional Patent Application
Commissioner for Patents
P.O. Box 1450
Alexandria, VA 22313-1450

(A) The attached document is filed as a Provisional Application for patent under 37 CFR 1.53 (c)(1).

(B) Inventors (including city and state or foreign country of residence, for each)
or alphanumeric identifier:

Richard M. Lange, 155 East 207th Street, Euclid, Ohio 44123

Stuart L. Bartley, 29954 Warren Road, Lakewood, Ohio 44107

Christian G. Ollinger, 513 Swindon Court, Spartanburg, South Carolina 29301

(C) Title: Maleated Vegetable Oils and Derivatives, as Self-Emulsifying Lubricants in Metalworking

(D) Attorney/Agent: Samuel B. Laferty Registration No. 31,537

(E) Docket Number: 3253

(F) Send Correspondence to: Docket Clerk
Patent Department/Mail Drop 022B
The Lubrizol Corporation
29400 Lakeland Blvd.
Wickliffe, Ohio 44092-2298

(G) Fees: Charge the fee for filing of a provisional application, believed to be \$160.00, to Deposit Account No. 12-2275 (The Lubrizol Corporation). Any deficiency or overpayment in fees should be charged or credited to the same account.

(H) 15 Pages of Specification
0 Pages of Drawings

3 Pages of Claims
1 Pages of Abstract

(I) A duplicate of this Cover Sheet is attached.

Registration No. 31,537
Telephone: 440-347-1541
Facsimile: 440-347-1110

Samuel B. Laferty
Attorney for Applicant

Samuel Laferty
Signature

Jan 09, 2004
Date

I certify that this correspondence is being deposited with the United States Postal Service as Express Mail No. EU381348278US in an envelope addressed to: Mail Stop Provisional Patent Application, Commissioner for Patents, P.O. Box 1450, Alexandria, Virginia 22313-1450 on January 9, 2004.

By: Nancy S. Dedek

Nancy S. Dedek

Date: 1/9/04

**TITLE: MALEATED VEGETABLE OILS AND DERIVATIVES, AS
SELF-EMULSIFYING LUBRICANTS IN METALWORKING**

5

FIELD OF THE INVENTION

[0001] The present invention relates to emulsifiers derived from maleating unsaturated triglyceride oils from vegetable sources and land animal sources. The reaction product is a succinated vegetable or animal oil. That reaction product can be further reacted with water, Group IA and IIA metals, ammonium hydroxide, various amines, alkanolamines, and polyamines to form other emulsifiers. The emulsifiers from succinated vegetable or animal oils are particularly useful in water based metalworking fluids.

15

BACKGROUND OF THE INVENTION

[0002] Mineral oils and vegetable oils are often used as components of formulated aqueous metalworking compositions. In these instances, a discreet emulsifying agent must be used to hold these non-polar, water insoluble oils in uniform suspension in the water matrix, and this adds significant cost to the commercial metalworking formulations. Additionally, not all types of emulsifying agents are equally effective in forming stable dispersions (emulsions) of vegetable oils in water, so it becomes critical to use the correct and most effective surfactant to accomplish this.

[0003] The patent literature contains a number of references to maleation of vegetable oils over the past 30 years, some of which may be pertinent, and this is currently being reviewed. Some early patents refer to thermal maleation, some describe the need to use polyunsaturated vegetable oils, some require catalysts to isomerize the two C=C bonds in linoleate moieties into conjugation to allow the Diels-Alder reaction with malan (maleic anhydride) to proceed, and some cite the use of radical initiators, and refer to the vegetable oils as "monomers", which is (in our opinion) inconsistent with chemical nomenclature.

[0004] Most of the applications described in the patent literature involve the use of the maleated vegetable oils in modifying the properties of air-cured alkyd coatings or to give flexibility and improved adhesion to substrates. Other applications include use in inks and coatings as aiding pigment dispersancy, and quite a few address their use in cosmetics and personal care products (emollients and skin softening). One Japanese patent (JP Pub. 4-73477) refers to maleated fish oil in a metalworking fluid.

[0005] It would be desirable to have functionalized natural oils for use in metalworking that are self-emulsifying.

SUMMARY OF THE INVENTION

[0006] The reaction product of maleating a triglyceride oil from a plant or land animal was unexpectedly found to be particularly useful emulsifier for oil in water emulsions. The reaction typically results in primarily mono-maleation under mole ratios of 1:1 between reactants, but with some percentage of di-maleation and possibly tri- or higher maleation being possible in still smaller amounts. The triglyceride oils are readily available in a variety of purities and readily undergo thermal maleation. The maleated products are often called succinated triglyceride oils because the maleic anhydride loses one carbon-to-carbon double bond in the thermal coupling reaction, while introducing it (i.e. converting the maleic acid or anhydride to a succinic acid or succinic anhydride substituent). In the present application, the terms "succination" and "maleation" can be used interchangeably to convey the concept and description of the natural oil functionalization.

[0007] We have found that these succinated triglycerides may be further reacted with water, Group IA and IIA metals, ammonium hydroxide, various amines, alkanolamines, and polyamines to form new emulsifiers that have different properties due to the addition of larger polar groups from the additional reactant.

[0008] Additionally, these functionalized triglyceride (natural) oils can self-emulsify, that is, form an instantaneous emulsion when added to water or other aqueous-based formulation. The nature and ease of formation of the

emulsions is dependent on both the extent (degree of) polar functionalization of the triglyceride oils and on the particular base oils used as the dispersed hydrophobic phase.

5 [0009] A preferred application for the succinated triglyceride oils are as emulsifiers in aqueous based metal working fluids. Historically alkyl benzene petroleum sulfonates have been used extensively in metalworking fluids due to their reasonable price, insensitivity to water hardness, good emulsifying capabilities, low tendency to foam, etc.. Various oils including vegetable oils were added to the metalworking fluids to provide lubricity during metalworking
10 operations. It has been found that the succinated triglyceride oils are particularly effective in emulsifying vegetable oil-containing metalworking fluids. The combination of vegetable or animal triglycerides and a functionalized vegetable or land animal triglyceride oil offers low foaming tendencies, good lubricity, low toxicity, and constitutes a novel and efficient
15 use for these polar-functionalized triglyceride oils.

DETAILED DESCRIPTION OF THE INVENTION

[0010] The reaction product of maleic anhydride and a triglyceride oil can be made by the thermal condensation of maleic anhydride or other
20 unsaturated carboxylic acid capable of undergoing either "Ene" or "Diels-Alder" adduction to the unsaturated sites in vegetable oils. The modified triglyceride oils become easily self-emulsifiable in water when treated with bases, and do not require any additional emulsifiers. Suitable bases to react with the reaction product of maleic anhydride and a triglyceride oil of a plant or
25 land animal include the Group IA and IIA metals, ammonium hydroxide, various amines, alkanolamines, and polyamines. A preferred triglyceride oil is a triglyceride oil of a plant or of a land animal.

[0011] The functionalized triglyceride oils (and their derivatives) described in this process comprise a class of self-emulsifiable lubricants which,
30 depending on their compositions, are also capable of acting as emulsifiers for other additives in the metalworking formulations. They are physically benign agents that help to stabilize emulsions, can add lubricity to the aqueous

emulsion formulations, and help to reduce corrosion, while facilitating machining and other metalworking operations. The products should also have a fairly high susceptibility to bio-degradation, particularly in emulsified media and thus are more environmentally friendly (more benign) than some other emulsifiers previously used in metalworking fluids.

[0012] The chemistry of manufacture of these self-emulsifying vegetable oils is relatively simple and straightforward. Attachment of maleic anhydride (preferred agent) may be carried out by thermal condensation at temperatures above 100 °C and preferably about 175-250°C, at the unsaturated C=C sites of the fatty acid moieties in the triglyceride oil.

[0013] The degree of maleic anhydride coupling to the triglyceride oil is a function of the oil composition and molar charge ratio of maleic anhydride to triglyceride oil. Oils comprising oleic acid esters can condense with maleic anhydride through an "Ene" mechanism ("Alder Reaction"), which involves the same type of electron transfer and subsequent 1,4-hydrogen migration common to the reaction of maleic anhydride with olefins and polyolefins, to form alkenylsuccinic anhydrides.

[0014] Triglyceride oils comprising high levels of linoleic acid esters can condense with maleic anhydride in a Diels-Alder manner, to form cyclohexene-dicarboxylic anhydride moieties. During thermal condensation, the two non-conjugated C=C bonds in the linoleic acid esters move into conjugation to form a 1,3-dienoic system, which easily undergoes 1,4-addition with the maleic anhydride C=C bond, to form a 4-cyclohexene-1,2-dicarboxylic anhydride near the midpoint of the linoleate ester "tail".

[0015] With the exception of coconut oil, which is mainly composed of saturated C12-C18 triglycerides, most domestic triglyceride oils from plants (oils from plants are commonly referred to as vegetable oils, a preferred starting material for this disclosure), contain various levels of both the unsaturated oleic and linoleic components. Coconut-derived palm oil and palm kernel oil both contain relatively high levels of saturated C12-14 triglycerides. They also have moderate levels (ca. 17-25%) of reactive oleic and linoleic esters, which can react with maleic anhydride.

[0016] High erucic rapeseed oil contains about 50% oleic, linoleic, and linolenic esters, and about 45% mono-unsaturated C22 acid ester, all of which can be thermally maleated.

Method and Process:

5 [0017] **Step A:** Triglyceride oils such as from vegetable sources and land animal sources [**component 1**] containing at least one reactive C=C double bond per molecule are charged to a suitable reaction vessel.

 [0018] **Step B:** Maleic anhydride or other unsaturated functional reagent [**component 2**] capable of acting as a dienophile, or of undergoing
10 "Ene" condensation, is charged to the vessel, and the mixture is stirred and heated to 175-250C. The mixture is held for 1-5 hours at final temperature to effect the condensations

- An inert atmosphere of nitrogen, CO₂, or other non-reactive gas can be used during the condensation, to promote the formation of lighter-colored
15 products.

- Additional stabilizers and antioxidants may also be optionally present to assure light colored products, and to prevent radical coupling of unsaturated moieties in the reaction mixture.

 [0019] A small amount (ca. 0.1-5.0%) of a compatibilizing solvent
20 [**component 3**] may be added, if desired, to promote contact between the polar maleic anhydride and the relatively non-polar olefinic "tails" of the triglyceride, and to inhibit loss of maleic anhydride by sublimation or entrainment at higher temperatures. Suitable solvents include toluene and certain low alkyl esters. During heating, the majority of solvent may be gradually removed from
25 reaction.

 [0020] **Step C:** The reaction mixture is sparged or vacuum-stripped after completion to remove solvent and unreacted maleic anhydride.

 [0021] **Step D:** Optionally, the stripped product may be cooled somewhat, and filtered for clarity through a simple cartridge filter, usually
30 without the use of filter aid.

 [0022] **The maleated intermediate** [**component 4**] is an anhydride (or carboxylic acid)-grafted vegetable oil which may be used directly as a self-

emulsifiable lubricity agent in aqueous emulsions, or which can be converted to esters, partial esters, amidic acids, amidic esters, imides, and other derivatives that are also useful in metalworking compositions, as lubricants, lubricity agents, friction modifiers, and antiwear agents.

5 **Reagents Used:**

[0023] Component 1. Triglyceride Oils

Includes triglycerides such as soybean oil ("SYBO"), rapeseed oil, canola oil, safflower oil, corn oil, chicken fat, butter oil, cottonseed oil, sunflower oil, high oleic sunflower oil, peanut oil, palm oil, palm kernel oil,
10 olive oil, and other natural oils derived from plants and land animals which contain measurable amounts of C=C unsaturation. Fully saturated triglycerides such as coconut oil are not included within the scope of these thermal functionalizations. Desirably at least 20 mole percent of the fatty acids of the triglyceride oil is unsaturated and more desirably at least 50 moles percent.

15 **[0024] Component 2. Unsaturated Acid or Anhydride Functionalizing Agent**

Maleic anhydride is the preferred component 2, but other unsaturated acids or anhydrides are also useful, including but not limited to, at least one of maleic acid, fumaric acid, itaconic acid and anhydride, acrylic acid, cinnamic
20 acid, and crotonic acid.

The amount of Component 2 used can be based on the degree and type of unsaturation in the vegetable oil, and the degree of functionalization (i.e., TAN) desired for the immediate purpose. On a molar basis, this would amount to a practical amount of from about 0.02-to-2.5 mole of maleic anhydride (more
25 broadly unsaturated acid or anhydride functionalizing agent) per mole of vegetable or land animal (natural) oil.

[0025] Component 3. The optional Compatibilizing Solvent

Suitable solvents are those which can dissolve maleic anhydride or other suitable unsaturated carboxylic acid, anhydride, ester, or amide, without
30 reacting with either the grafting agent or the vegetable oil substrate. Preferably they are volatile so they can be easily removed either during, or after reaction is

complete. Examples of solvents include cyclohexane, toluene and similar lower alkyl aromatics, ketones and low alkyl esters.

The amount of **Component 3** useful in these processes is generally low, on the order of about 0.1% to about 5%, based on the amount of natural oil.

5 **Derivatives of the Functionalized Vegetable Oils**

[0026] **Carboxylic Acids:** The maleated intermediates (component 4) may be reacted with water, generally in the amount of about 1 mole per anhydride present. Mono-maleated vegetable oils will yield dicarboxylic acids, di-maleated vegetable oils will yield tetra-carboxylic acids, etc.

10 [0027] **Esters:** Reaction of maleated intermediates with alcohols produces esters. Depending on the amount of ester linkages desired and the desire or lack thereof the amount of alcohols can vary from a molar ratio of alcohol to succinate groups on the maleated intermediate from about 0.1 (only about 10% of the succinate groups would partially esterified) to about 2 (where
15 near about 100% of the succinate groups would be esterified). The presence of polyfunctional alcohols, amines, or alkanol amines further complicates things as polyfunctional alcohols (or amines or some alkanolamines) can serve as coupling agents for the maleated intermediate. Alkanolamines may also partially salt (either internally (alcohol of alkanolamine forms ester linkage for one carboxylic acid of succinic anhydride or acid as amine of alkanolamine
20 forms salt with the remaining carboxylic acid on the same succinic molecule) or externally (alcohol portion of alkanolamine not otherwise associated with succinic acid group which is salted by the amine of the alkanolamine)). These alcohols can include (but are not limited to) alkanolamines; amine ethoxylates; monohydric alcohols, diols, and polyols; condensation products of polyols; and poly(alkylene oxide) and its derivatives. Reaction of one mole of alcohol per anhydride gives half-esters/half acids, which can be easily emulsified in water, using bases. Reaction with greater amounts of alcohols can produce mixtures of diesters and half-esters within the same molecule. Alkoxylated
25 amines can react with the anhydride groups to produce aminoalkyl esters, which may be emulsified or dispersed in water. Alkoxylated amines may be reacted with ethylene oxide or propylene oxide to form ethoxylates that can be
30

coupled to the succinated vegetable oils. These ethoxylated or propoxylated amines can dramatically change the water solubility of the succinated vegetable oils.

5 [0028] **Amidic Acids and Imides:** Reaction of the anhydride portion of the maleated intermediates with **secondary amines** produces N,N-dialkyl amidic acids, which can be easily emulsified in water by treatment with bases. Reaction of the anhydride with **primary amines** will initially produce N-alkyl amidic acids, which may close down to produce imide functions. Depending on the nature of the primary amine used, the vegetable oil imides may, or may not
10 be water-dispersible. [0029] **Polyetheramines** such as the commercial "Jeffamines" from Huntsman, or those from Tomah, can produce water-dispersible amidic acid and imide derivatives.

[0029] The maleated vegetable oils and their derivatives can be easily self-emulsified in water by treatment with bases, and are useful at levels of
15 about 0.5 or 1 to about 10 weight percent, more desirably from about 2 to about 8 weight percent as lubricity agents and additives for metalworking.

TABLES 1 and 2 (see Appendix 1 and 2)

EXAMPLES

[0030] **Example 1: Soybean oil/maleic anhydride/triethanolamine**
20 **(1:1:1) mole**

With stirring and under a nitrogen atmosphere, maleic anhydride is reacted with soybean oil on a one-to-one mole basis at 220°C for four hours to form the maleated soybean oil. A small amount of toluene (0.25% wt) is added prior to heating so that the maleic anhydride will not sublime and be lost.
25 When cooled, this intermediate is further reacted with one mole of triethanolamine for every mole of maleated soybean oil at 50°C for one hour to form the ester. The resulting functionalized soybean oil self-emulsifies well in water when mixed at 5% in water and has an approximate pH of 8.4. Emulsion testing using the IP 263 method (at 5% treat level) showed no oil or cream
30 formation in synthetic 400 ppm CaCO₃ water at 40°C after 24 hours. Foaming tests (by method IP 312) on the 5% in water emulsion showed that foam collapse was quite significant.

[0031] Example 2: Rapeseed oil/maleic anhydride/monoethanolamine (1:1:2) mole

With stirring and under a nitrogen atmosphere, Maleic anhydride is reacted with rapeseed oil on a one-to-one mole basis at 220 °C for four hours to form the maleated rapeseed oil. A small amount of toluene (0.25% wt) is added prior to heating so that the maleic anhydride will not sublime and be lost. When cooled, this intermediate is further reacted with two moles of monoethanolamine at 40°C (exotherm occurs so the addition of monoethanolamine is added over a one-hour period) and heated ~ 50°C for an additional hour after all the monoethanolamine is added to form the partial ester-amide-salt. The resulting functionalized rapeseed oil self-emulsifies well in water when mixed at 5% in water and has an approximate pH of 10.0. Emulsion testing using the IP 263 method (at 5% treat level) showed no oil and approximately 1.4 mL of cream formation in synthetic 400 ppm CaCO₃ water at 40°C after 24 hours. This functionalized rapeseed oil demonstrated that it can also serve as an emulsifier for paraffinic and naphthenic oils in an aqueous medium.

[0032] The anti-misting polymer of US 6,100,225, hereby incorporated by reference for its teaching on its antimist agent, is a useful additive in this formulation. It or other polymeric anti-mist agents can be used in a concentration range of 0.02 weight percent to 10 weight percent based upon the total weight of the composition.

[0033] In addition to the anti-misting polymer, the aqueous metal working fluids may contain additives to improve the properties of the composition. These additives include anti-foam agents, metal deactivators, and corrosion inhibitors, antimicrobial, anticorrosion, extreme pressure, antiwear, antifriction, and antirust agents. Such materials and the relative amounts used in metalworking fluids are well known to those skilled in the art.

[0034] The metal working fluids of the present invention may also be oil-in-water emulsions. The emulsion compositions metalworking fluids contain the same types and amounts of optional additives as the purely aqueous compositions discussed above. The particular maleated triglyceride oils of this

application show enhancements over other purely aqueous metalworking compositions due to the inherent lubricity of the maleated triglyceride oils relative to other emulsifiers for these fluids. The compositions may also contain the property improving additives which have been used in the purely aqueous fluids.

[0035] The oils used in the emulsion compositions may include vegetable oils as previously defined including triglyceride oils from animals, petroleum oils, such as oils of lubricating viscosity, crude oils, diesel oils, mineral seal oils, kerosenes, fuel oils, white oils, naphthenic oils, and aromatic oils. Liquid oils include natural lubricating oils, such as (land) animal oils, vegetable oils, mineral lubricating oils, solvent or acid treated mineral oils, oils derived from coal or shale, and synthetic oils. Synthetic oils include hydrocarbon oils and halo-substituted hydrocarbon oils such as polymerized and interpolymers of olefins, for example polybutylenes, polypropylenes, propylene-isobutylene copolymers, chlorinated polybutylenes, poly(1-hexenes), poly(1-octenes), poly(1-decenes); alkyl benzenes, such as dodecylbenzenes, tetradecylbenzenes, dinonylbenzenes, di-(2-ethylhexyl)benzenes; polyphenyls such as biphenyls, terphenyls, and alkylated polyphenyls; and alkylated diphenyl ethers and alkylated diphenyl sulfides and derivatives, analogs and homologs thereof. Vegetable oils and triglyceride oils from animals are preferred in some applications due to their biodegradability and benign effect on most water treatment processes and ecosystems.

[0036] Alkylene oxide polymers and derivatives thereof where terminal hydroxy groups have been modified by esterification, etherification etc. constitute another class of synthetic oils. These are exemplified by polyoxyalkylene polymers prepared by the polymerization of ethylene oxide or propylene oxide, the alkyl and aryl ethers of these polyoxyalkylene polymers such as methyl-polyisopropylene glycol ethers, diphenyl and diethyl ethers of polyethylene glycol; and mono and polycarboxylic esters thereof, for example, the acetic esters, mixed $C_3 - C_8$, fatty acid esters and C_{13} OxO diester of tetraethylene glycol. Simple aliphatic ethers may be used as synthetic oils, such as, dioctyl ether, didecyl ether, di(2-ethylhexyl) ether.

[0037] Another suitable class of synthetic oils comprises the esters of fatty acids such as ethyl oleate, lauryl hexanoate, and decyl palmitate. The esters of dicarboxylic acids such as phthalic acid, succinic acid, maleic acid, azelaic acid, sebacic acid, fumaric acid, adipic acid, linoleic acid dimer, malonic acid, alkyl malonic acids, alkenyl malonic acids with a variety of alcohols such as butyl alcohol, hexyl alcohol, dodecyl alcohol, 2-ethylhexyl alcohol, ethylene glycol, diethylene glycol monoethyl ether, propylene glycol. Specific examples of these esters include dibutyl adipate, di(2-ethylhexyl) sebacate, di-n-hexyl fumarate, dioctyl sebacate, diisooctyl azelate, dioctyl phthalate, didecyl phthalate, dieicosyl sebacate, the 2-ethylhexyl diester of linoleic acid dimer, and the complex ester formed by reacting one mole of sebacic acid with two moles of tetraethylene glycol and two moles of 2-ethylhexanoic acid.

[0038] The ratio of oil to water in the final formulated metalworking fluid (if oil is present) may vary from about 1:5 to about 1:200. Other oil-in-water emulsifier may be used supplementally (for particular performance characteristics) in preparing the emulsions of the present invention. Emulsifiers may be single materials or may be mixtures of surfactants. General emulsifiers include alkali metal sulfonates and carboxylates, salts derived from the reaction product of carboxylic acylating agents with amines and hydroxylamines, polyols, polyether glycols, polyethers, and polyesters and the like. *The Kirk-Othmer Encyclopedia of Chemical Technology* (3rd. Edition V. 8 pp. 900 - 930) provides a good discussion of emulsions and provides a list of emulsifiers useful in preparation of oil-in-water emulsions.

[0039] A typical metal working fluid would include other components such as anti-foam agents, metal deactivators, corrosion inhibitors, antimicrobial, extreme pressure, antiwear, antifriction, and antirust agents. Typical anti-friction agents include overbased sulfonates, sulfurized olefins, chlorinated paraffins and olefins, sulfurized ester olefins, amine terminated polyglycols, and sodium dioctyl phosphate salts. Useful anti-foam agents include: alkyl polymethacrylates, and polymethylsiloxanes. Metal deactivators include materials such as tolyltriazoles. Corrosion inhibitors include

carboxylic/boric acid diamine salts, carboxylic acid amine salts, alkanol amines, alkanol amine borates and the like.

5 [0040] As used herein, the term "hydrocarbyl substituent" or "hydrocarbyl group" is used in its ordinary sense, which is well-known to those skilled in the art. Specifically, it refers to a group having a carbon atom directly attached to the remainder of the molecule and having predominantly hydrocarbon character.

10 [0041] Examples of hydrocarbyl groups include: (1) hydrocarbon substituents, that is, aliphatic (e.g., alkyl or alkenyl), alicyclic (e.g., cycloalkyl, cycloalkenyl) substituents, and aromatic-, aliphatic-, and alicyclic-substituted aromatic substituents, as well as cyclic substituents wherein the ring is completed through another portion of the molecule (e.g., two substituents together form a ring);

15 [0042] (2) substituted hydrocarbon substituents, that is, substituents containing non-hydrocarbon groups which, in the context of this invention, do not alter the predominantly hydrocarbon substituent (e.g., halo (especially chloro and fluoro), hydroxy, alkoxy, mercapto, alkylmercapto, nitro, nitroso, and sulfoxy);

20 [0043] (3) hetero substituents, that is, substituents which, while having a predominantly hydrocarbon character, in the context of this invention, contain other than carbon in a ring or chain otherwise composed of carbon atoms. Heteroatoms include sulfur, oxygen, nitrogen, and encompass substituents as pyridyl, furyl, thienyl and imidazolyl. In general, no more than two, preferably no more than one, non-hydrocarbon substituent will be present for every ten
25 carbon atoms in the hydrocarbyl group; typically, there will be no non-hydrocarbon substituents in the hydrocarbyl group.

30 [0044] It is known that some of the materials described above may interact in the final formulation, so that the components of the final formulation may be different from those that are initially added. For instance, metal ions can migrate to other acidic sites of other molecules. The products formed thereby, including the products formed upon employing the composition of the present invention in its intended use, may not be susceptible of easy description.

Nevertheless, all such modifications and reaction products are included within the scope of the present invention; the present invention encompasses the composition prepared by admixing the components described above.

[0045] Each of the documents referred to above is incorporated herein
5 by reference. Except in the Examples, or where otherwise explicitly indicated, all numerical quantities in this description specifying amounts of materials, reaction conditions, molecular weights, number of carbon atoms, and the like, are to be understood as modified by the word "about." Unless otherwise
10 indicated, each chemical or composition referred to herein should be interpreted as being a commercial grade material which may contain the isomers, by-products, derivatives, and other such materials which are normally understood to be present in the commercial grade. However, the amount of each chemical component is presented exclusive of any solvent or diluent oil which may be customarily present in the commercial material, unless otherwise indicated. It
15 is to be understood that the upper and lower amount, range, and ratio limits set forth herein may be independently combined. As used herein, the expression "consisting essentially of" permits the inclusion of substances which do not materially affect the basic and novel characteristics of the composition under consideration.

3253

What is claimed is:

- 5 1. An emulsifier for forming an oil in water emulsion comprising
 - a) a reaction product of maleic anhydride and a triglyceride oil from a
plant or land animal
 - b) further reacted with water, Group IA and IIA metals, ammonium
hydroxide, various amines, alkanolamines, polyols, alkoxylated
10 alkanolamines, poly(alkylene oxide)s, or polyamines or mixtures
thereof to form an emulsifier.
2. An emulsifier according to claim 1, wherein there is an average of 0.1 to 2
mole of succinate groups per mole of triglyceride oil.
- 15 3. An emulsifier according to claim 2, wherein said reaction product is
reacted with an alkanolamine.
4. An emulsifier according to claim 2, wherein said reaction product is
20 reacted with a polyamine.
5. An emulsifier according to claim 2, wherein said reaction product is
reacted with ammonium hydroxide.
- 25 6. An emulsifier according to claim 2, wherein said reaction product is
reacted with triethanolamine.
7. A metalworking fluid comprising;
 - a) a reaction product of maleic anhydride and a triglyceride oil from a
plant or land animal, optionally further reacted with water, Group IA
and IIA metals, ammonium hydroxide, various amines, alkanolamines,
30 and polyamines to form an emulsifier,

- b) a major amount of water, and
- c) optionally an oil selected from the group consisting of triglyceride oils, hydrocarbon oils (aliphatic, aromatic, petroleum distillates, poly(alpha olefins), Fischer Tropsch oils, etc), and ester oils other than triglyceride oils.

5

8. A metalworking fluid according to claim 7, wherein said reaction product is present in an amount from about 0.5 to about 10 weight percent based on the weight of said fluid.

10

9. A metalworking fluid according to claim 8, wherein said reaction product has from about 0.1 to about 2 mole of succinate groups per mole of triglyceride oil.

15

10. A metalworking fluid according to claim 8, further comprising at least one of a corrosion inhibiting agent and/or a antiwear agent.

11. A metalworking fluid according to claim 10, further comprising an extreme pressure agent.

20

12. A metalworking fluid according to claim 10, further comprising a biocide.

13. A metalworking fluid according to claim 7, wherein said optional oil is present from about 1 to about 50 weight percent based on the weight of said metalworking fluid.

25

14. A metalworking fluid according to claim 8, wherein said reaction product of maleic anhydride and triglyceride oil forms a succinated triglyceride oil which is then is reacted with an alkanolamine to form some a) ester linkages between the succinic acid of said succinated triglyceride and the alcohol of the alkanolamine and b) some salts of the succinic acid of said succinated triglyceride and the nitrogen atom of the alkanolamine.

30

15. A metalworking fluid according to claim 14, wherein said alkanolamine comprises triethanolamine.

5 16. A metalworking fluid according to claim 14, wherein said alkanolamine comprises an ethoxylated triethanolamine.

10 17. A metalworking fluid according to claim 14, wherein said alkanolamine comprises an alkanolamine with two alcohol substituents and one alkyl substituent or two alkyl substituents and one alcohol substituent.

15 18. A metalworking fluid according to claim 7, wherein said reaction product of maleic anhydride and a triglyceride oil comprises both the reaction product of a first triglyceride oil and maleic anhydride and the reaction product of a second different triglyceride oil and maleic anhydride.

20 19. A metalworking fluid according to claim 7, wherein said component c) comprises a triglyceride oil of a plant or land animal that hasn't been reacted with maleic anhydride.

25 20. A metalworking fluid according to claim 7, where said reaction product of maleic anhydride and a triglyceride oil from a plant or land animal is further reacted with an ethoxylated or propoxylated alkanolamine forming a half-ester salt.

3253

ABSTRACT

5 A succinated triglyceride oil derived from maleating triglyceride oil
from a plant or land animal is described for use as an emulsifying agent for
metalworking fluids. The metalworking fluid would comprise water; as an
emulsifier this succinated triglyceride, optionally further reacted with water,
Group IA and IIA metals, ammonium hydroxide, various amines,
10 alkanolamines, alkoxylated alkanolamines, and polyamines to form a modified
emulsifier; optionally an oil, and optionally other additives.

From the INTERNATIONAL BUREAU

PCTNOTIFICATION CONCERNING
SUBMISSION OR TRANSMITTAL
OF PRIORITY DOCUMENT

(PCT Administrative Instructions, Section 411)

To:

GILBERT, Teresan, W.
The Lubrizol Corporation
Patent Dept./Mail Drop 022B
29400 Lakeland Blvd.
Wickliffe, OH 44092-2298
ETATS-UNIS D'AMERIQUE

Date of mailing (day/month/year) 28 February 2005 (28.02.2005)	
Applicant's or agent's file reference 3253-01-WO	IMPORTANT NOTIFICATION
International application No. PCT/US05/000487	International filing date (day/month/year) 07 January 2005 (07.01.2005)
International publication date (day/month/year)	Priority date (day/month/year) 09 January 2004 (09.01.2004)
Applicant THE LUBRIZOL CORPORATION et al	

- By means of this Form, which replaces any previously issued notification concerning submission or transmittal of priority documents, the applicant is hereby notified of the date of receipt by the International Bureau of the priority document(s) relating to all earlier application(s) whose priority is claimed. Unless otherwise indicated by the letters "NR", in the right-hand column or by an asterisk appearing next to a date of receipt, the priority document concerned was submitted or transmitted to the International Bureau in compliance with Rule 17.1(a) or (b).
- (If applicable)* The letters "NR" appearing in the right-hand column denote a priority document which, **on the date of mailing of this Form**, had not yet been received by the International Bureau under Rule 17.1(a) or (b). Where, under Rule 17.1(a), the priority document must be submitted by the applicant to the receiving Office or the International Bureau, but the applicant fails to submit the priority document within the applicable time limit under that Rule, the attention of the applicant is directed to Rule 17.1(c) which provides that no designated Office may disregard the priority claim concerned before giving the applicant an opportunity, upon entry into the national phase, to furnish the priority document within a time limit which is reasonable under the circumstances.
- (If applicable)* An asterisk (*) appearing next to a date of receipt, in the right-hand column, denotes a priority document submitted or transmitted to the International Bureau but not in compliance with Rule 17.1(a) or (b) (the priority document was received after the time limit prescribed in Rule 17.1(a) or the request to prepare and transmit the priority document was submitted to the receiving Office after the applicable time limit under Rule 17.1(b)). Even though the priority document was not furnished in compliance with Rule 17.1(a) or (b), the International Bureau will nevertheless transmit a copy of the document to the designated Offices, for their consideration. In case such a copy is not accepted by the designated Office as the priority document, Rule 17.1(c) provides that no designated Office may disregard the priority claim concerned before giving the applicant an opportunity, upon entry into the national phase, to furnish the priority document within a time limit which is reasonable under the circumstances.

<u>Priority date</u>	<u>Priority application No.</u>	<u>Country or regional Office or PCT receiving Office</u>	<u>Date of receipt of priority document</u>
09 January 2004 (09.01.2004)	60/535,330	US	18 February 2005 (18.02.2005)

The International Bureau of WIPO
34, chemin des Colombettes
1211 Geneva 20, Switzerland

Facsimile No. +41 22 740 14 35

Authorized officer

Giffo Schmitt Beate

Facsimile No. +41 22 338 87 20

Telephone No. +41 22 338 9241